



DESIGN SOLUTION RESTAURANTS

PROJECT

Raffa's American Bistro
Kingwood, TX

DETAILS

K-13® Black
1.5" Thick
7,000 sq. ft.



Raffa's American Bistro is the first restaurant to open in the King's Harbor Waterfront Development located in Kingwood, TX. The interior is spacious with soaring 25 foot ceilings and 12 foot windows that overlook the water and the plaza. With this stylish architecture design and rooms that accommodate 160 patrons, it quickly became clear that they had an acoustical

problem. The owners needed an acoustical product that eliminates the reverberation and provides an attractive exposed ceiling. K-13 black was applied 1.5 inches thick to the ceiling area to provide an NRC of .90 and did not interfere with the architectural design.

K-13 is available in six standard colors: Black, Lt Gray, White, Gray, Tan and Beige. Custom colors are also available, call International Cellulose for details.

Churches, warehouses, restaurants, gymnasiums, retail facilities, sports facilities, and schools are just a few of the many types of projects that benefit from K-13. Contact International Cellulose Corporation today at (800) 444-1252, or visit us online at www.spray-on.com for complete details on how ICC can improve your building projects.

SIMILAR K-13 PROJECTS

STARBUCK'S COFFEE
NEW YORK, NY

CAFE EXPRESS
DALLAS, TX

TERRA BISTRO RESTAURANT
VAIL, CO

QOBBA MEXICAN GRILL
LEXINGTON, KY

CHIMICHURRI'S
KINGWOOD, TX

HARD ROCK CAFE
PHOENIX, AZ

CITY STREETS
DALLAS, TX

EL DORADO BAR
COLUMBUS, OH

KONA GRILL
KANSAS CITY, MO

BACKYARD GRILL
PLANO, TX

SOUTH CITY GRILL
JERSEY CITY, NJ

LORAINÉ'S LUNCH BASKET
ROCHESTER, NY

SCOTTIE'S BREW HOUSE
MUNCIE, IN

MAMACITA'S RESTAURANT
SAN ANTONIO, TX

TORTILLA JOE'S AT DISNEYLAND
AHAHEIM, CA

HOUSE OF BLUES
DALLAS, TX

K-13® Spray On Systems Section 072129 Specification Guide 05/09

PART 1 – GENERAL

1.01 Section Includes

- A. Sprayed cellulose thermal insulation.
- B. Sprayed cellulose acoustical insulation.

1.02 Related Items

- A. Clips, hangers, supports, sleeves and other attachments to spray bases are to be placed by other trades prior to the application of sprayed insulation.
- B. Ducts, piping, conduit or other suspended equipment shall not be positioned until after the application of sprayed insulation.
- C. Roof penetrations to be installed prior to application.

1.03 Quality Assurance

- A. Manufacturer must have a current listing with ICC.
- B. Manufacturer must be in compliance with the 2006 International Building Code.
- C. Manufacturer must be ISO 9001:2008 Certified.
- D. Applicator: Licensed by manufacturer.
- E. Manufacturer must subscribe to independent laboratory follow-up inspection services of Underwriters Laboratories and Factory Mutual. Each bag shall be labeled accordingly.
- F. Mock-up: Apply a 100 square foot representative sample to be reviewed by the Architect and/or Owner prior to proceeding.

1.04 Submittals

- A. Submit product data that the product meets or exceeds the following specified requirements.
 1. R-Value shall be 3.8 per inch per ASTM C 518.
 2. Bond strength shall be greater than 100 psf per ASTM E 736.
 3. Product shall be Class 1 Class A per ASTM E 84/UL 723.
 4. Non-corrosive per ASTM C 739.
 5. Bond Deflection per ASTM E 759: 6" Deflection in 10' Span - No Spalling or Delamination
- B. Manufacturer's written certification that product contains no asbestos, fiberglass or other man-made mineral fibers.
- C. Copy of manufacturer's ISO 9001:2008 Certification.
- D. Minimum Fiber Recycled Content to be 75%.
- E. Cannot contain any Urea-Formaldehyde Resins.

1.05 Delivery, Storage and Handling

- A. Deliver in original, unopened containers bearing name of manufacturer, product identification and reference to U.L. testing.
- B. Store materials dry, off ground, and under cover.
- C. Protect liquid adhesive from freezing.

PART 2 – PRODUCTS

2.01 Acceptable Manufacturers

- A. International Cellulose Corporation
12315 Robin Boulevard
Houston, Texas 77045
(713) 433-6701 or (800) 444-1252
FAX: (713) 433-2029
Email: icc@spray-on.com
www.spray-on.com
- B. For approved applicators contact ICC at 800-444-1252.

2.02 Materials

- A. K-13 Spray-On-Systems.

1. Color shall be from Manufacturer's standard color chart.
2. Comply with local Building Code requirements.
3. Material to have been tested in accordance with ASTM E 1042. Testing laboratory must be NVLAP accredited.

PART 3 – EXECUTION

3.01 Examination

- A. Examine surfaces and report unsatisfactory conditions in writing. Do not proceed until unsatisfactory conditions are corrected.
- B. Verify surfaces to receive spray insulation to determine if priming/sealing is required to insure bonding and/or to prevent discoloration caused by migratory stains.

3.02 Preparation

- A. Provide masking, drop cloths or other satisfactory coverings for materials/surfaces that are not to receive insulation to protect from over-spray.
- B. Coordinate installation of the sprayed cellulose fiber with work of other trades.
- C. Prime surfaces as required by manufacturer's instructions or as determined by examination.

3.03 Installation

- A. Thickness will be determined as the minimum thickness measured as per ASTM E-605 field test procedure.
- B. Install spray applied insulation according to manufacturer's recommendations.
- C. Install spray applied insulation to achieve an R-Value of ____.
(maximum of R 19)
- D. Install spray applied insulation to achieve an overall NRC of ____.

K-13 Sprayed Thermal and Acoustical Insulation ASTM C-423 on Solid Backing*							
Inches	125 HZ	250 HZ	500 HZ	1000 HZ	2000 HZ	4000 HZ	NRC
1.00	0.08	0.29	0.75	0.98	0.93	0.96	0.75
1.00**	0.47	0.90	1.10	1.03	1.05	1.03	1.00
2.00	0.26	0.68	1.05	1.10	1.03	0.98	0.95
3.00	0.57	0.99	1.04	1.03	1.00	1.00	1.00

K-13 Sprayed Thermal and Acoustical Insulation Applied at 1.5" Ribbed Metal Deck*							
Inches	125 HZ	250 HZ	500 HZ	1000 HZ	2000 HZ	4000 HZ	NRC
1.50	0.36	0.89	1.26	1.07	1.01	1.00	1.05
3.00	0.97	1.04	1.13	0.99	0.95	0.98	1.05

*Some values interpolated

**On lath

- E. Cure insulation with continuous natural or mechanical ventilation.
- F. Remove and dispose of over-spray.

3.04 Protection

- A. Protect finished installation under provision of Division 1.



12315 ROBIN BLVD.
HOUSTON, TX 77045
Office: (800) 444-1252 or (713) 433-6701
Fax: (713) 433-2029
E-mail: icc@spray-on.com
www.spray-on.com

© 2009 ICC ALL RIGHTS RESERVED.

Professionally installed by:



K-13® is manufactured with:
Minimum 80% recycled content

PRINTED IN USA 10/09:



10%
TOTAL RECOVERED FIBER
ALL POST-CONSUMER FIBER



Mixed Sources
Product group from well-managed forests, controlled sources and recycled wood or fiber
www.fsc.org Cert no. SW-COC-001530
© 1996 Forest Stewardship Council